

Model: DEEP WHITE NATURE L9 59,6X59,6(A) Codes: 100350401 Water absorption: Bla - Porcelanico (E<=0.1%)



Sistema DAPc<sup>®</sup> Declaración Ambiental de Productos de Construcción

	DIMENSIONAL FEATURES UNE-EN ISO 10545-2	
Thickness	9.5 MM	+/-5%*
Width	596 MM	
Length	596 MM	
Length and width deviation	Below 0.15%	+/-0.3%*
Side straightness deviation	Below 0.15%	+/-0.3%*
Squareness deviation	Below 0.15%	+/-0.3%*
Surface flatness deviation	Below 0.15%	+/-0.4%*
*ISO-13006:2018 UNE-EN 14411:2016		
	MECHANICAL FEATURES UNE-EN ISO 10545-4-6-7-11	
Breaking strength	3055.6 N	>1300N*
Modulus of rupture	57.9 N/MM2	>=35N/mm2*
Crazing resistance	Resists 3 cycles	
*ISO-13006:2018 UNE-EN 14411:2016		
Chemical resistance	HYGIENIC FEATURES UNE-EN ISO 10545-13-14:1995 Class "A" for swimming pools and cleaning products	B Min.*
Chemical resistance	(resists attack). Minimum Class "B" for acids and bases	d Will.
Stain resistance	Class 5. Easy cleaning with water	3 Min.*
*ISO-13006:2018 UNE-EN 14411:2016		
	ANTI-SLIP VALUE EN 16165: 2022 / ASTM C1028	
Dynamic coefficient of friction	>0,42	
Slip resistance (pendulum-wet)	CL1	
*ISO-13006:2018 UNE-EN 14411:2016		
	PACKING	
Sales units per box	1.420858 M2/BOX	
Sales units per pallet	45.467462 M2/PAL	
Sales units per unit	0.355215 M2/PIECE	
	SCOPE OF USE	
Technical code-1	7 - Use on heavy traffic floors	

System Certification



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

## PORCELANOSA Grupo

## RECOMMENDED USE LOCATIONS

RECOMMENDED USE LOCATIONS		
Single-family dwelling		
Outdoor Premises: Porches, verandah, terrace, outdoor access or circulation area		
Indoor Premises - Dry: Entrance and other enclosures with direct opening to the outside (garden, terrace, storage room).		
Indoor Premises - Dry: Individual staircase		
Indoor Premises - Dry: Garage, Covered Parking Area		
Indoor Premises - Wet: Kitchen, mini kitchen in living area, laundry room		
Indoor Premises - Humid: Bathroom or Toilet		
Collective housing		
Outdoor premises: Balconies, terraces, galleries (not accessible from the outside)		
Indoor Premises - Common Elements: Entrance Hall (less than 15 dwellings)		
Interior Premises - Common Elements: Entrance Hall (more than 15 dwellings)		
Indoor Premises - Common Elements: Stairs and corridors with or without lifts		
Indoor Premises - Common Elements: Meter centralisation room		
Indoor Premises - Common Elements: Storage rooms for children's cars, bicycles, etc.		
Indoor Premises - Dwelling - Damp: Kitchen, mini kitchen and living area, laundry room		
Indoor Premises - Dwelling - Damp: Bathrooms or shower rooms		
Public Residential		
Single or double rooms		
Group rooms		
Intensive use dormitories in residences, schools, etc.		
Administrative		
Office with workstation		
Collective office, open plan office		
Meeting/conference room, shops and retail (sales area)		
Shops, warehouses with average public attendance (sales area)		
Department stores, hypermarkets, shopping centres (sales area)		
Department stores, hypermarkets, shopping centres (warehouse, loading and unloading areas)		
Commercial		
Shops and retail trade (Sales area)		
Shops, warehouses with average public attendance (sales area)		
Department stores, shopping centres (sales area)		
Hypermarkets (Sales area)		
Teacher		
Pre-school and Primary: Classroom without direct opening to the exterior		
Infant and Primary: Playroom, exercise, multi-purpose room without direct opening to the outside.		
Secondary, Baccalaureate and University: Classroom without direct opening to the outside.		
Secondary, Baccalaureate and University: Multi-purpose classroom, meetings		
Secondary, Baccalaureate and University: Other laboratories (physics, electricity, radiation, mechanics).		
Sanitary		
Single-user room, isolation room		
Collective room		
Waiting rooms, consultation rooms, distribution corridors		
Major and minor operating theatres. Operating theatres		
Radiological premises		
Rehabilitation, massage, therapy and rehabilitation centres		
Laboratories (no public access)		
Public attendance		
Catering: Main dining room, banqueting hall (intensive use)		
Catering: Dining room restaurant, bar, cafeteria (medium use)		
Catering: Dining room, company cafeteria		
Entertainment and recreation: Large hall for receptions, dances, discotheques. Intensive use		
Entertainment and recreation: Showroom, cinema, theatre, sports activities, amphitheatres, games (Closed)		



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.



Entertainment and recreation: lounges, waiting room, TV lounge, games room

Libraries and reading rooms: Libraries, reading rooms, temples of worship, museums (With public access)

Libraries and reading rooms: Libraries, reading rooms, houses of worship, museums (Internal use)

## Common transit areas

Indoor premises: corridors and common areas with heavy traffic

Indoor premises: Corridors and common areas with average traffic

## Service. facilities

Toilets in office areas, restricted use

Sanitary premises special hygiene (hospitals, food)

Premises for telephone, computer and other dry installations

Re-printing service, copies of plans, photography

Archive and storage premises

Heavy storage premises with handling of loads



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.