

Model: MINNESOTA HONEY 23X150(A) Codes: 100339716 Water absorption: BIa - Porcelanico (E<=0.1%)





DIMENSIONAL FEATURES UNE-EN ISO 10545-2				
Thickness	11 MM	+/-5%*		
Width	230 MM			
Length	1500 MM			
Length and width deviation	Below 0.15%	+/-0.3%*		
Side straightness deviation	Below 0.15%	+/-0.3%*		
Squareness deviation	Below 0.15%	+/-0.3%*		
Surface flatness deviation	Below 0.15%	+/-0.4%*		
*ISO-13006:2018 UNE-EN 14411:2016				

	MECHANICAL FEATURES UNE-EN ISO 10545-4-6-7-11	
Breaking strength	3370 N	>1300N*
Modulus of rupture	50 N/MM2	>=35N/mm2*
Abrasion resistance	PEI 3 / 600v	
Crazing resistance	Resists 3 cycles	
*ISO-13006:2018 UNE-EN 14411:2016		

	HYGIENIC FEATURES UNE-EN ISO 10545-13-14:1995	
Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	B Min.*
Stain resistance *ISO-13006:2018 UNE-EN 14411:2016	Class 5. Easy cleaning with water	3 Min.*

	ANTI-SLIP VALUE EN 16165: 2022 / ASTM C1028	
Slip resistance (pendulum-wet)	CL1	
*ISO-13006:2018 UNE-EN 14411:2016		
	PACKING	
Sales units per box	1.724971 M2/BOX	
Sales units per pallet	41.399296 M2/PAL	
Sales units per unit	0.344994 M2/PIECE	
	SCOPE OF USE	
Technical code-1	5 - Use on medium traffic floors	

System Certification



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

PORCELANOSA Grupo

RECOMMENDED USE LOCATIONS

Single-family dwelling

Indoor Premises - Dry: Room, room, bedroom or other enclosure without direct access to the outdoors.

Collective housing

Indoor Premises - Residential - Dry: Entrance, living room, dining room, professional office with reception of customers

Indoor Premises - Housing - Dry: Bedrooms, personal office, storage room, changing room

Various

Cladding of bonded or mixed facades

Facade cladding with mechanical anchors

Kitchen worktops, bars, restaurants

Public bathroom countertops



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.