

Model: NYLO NOIR POL. 120X270(6)(A) Codes: 100332628 Absorption: Bla - Porcelanico (E<=0.1%)





DIMENSIONAL FEATURES UNE-EN ISO 10545-2				
Length	2700 MM			
Thickness	6 MM			
Width	1200 MM			
Length and width deviation	Below 0.15%	+/-0.3%*		
Side straightness deviation	Below 0.15%	+/-0.3%*		
Squareness deviation	Below 0.15%	+/-0.3%*		
Surface flatness deviation	Below 0.15%	+/-0.4%*		
*ISO-13006:2015 UNE-EN 14411:2017				

MECHANICAL FEATURES UNE-EN ISO 10545-4-6-7-11				
Breaking strenght	>1100 N			
Modulus of rupture	>45 N/MM2			
Abrasion resistance	<140			
*ISO-13006:2015 UNE-EN 14411:2017				

HYGIENIC FEATURES UNE-EN ISO 10545-13-14		
Chemical resistance	MIN B	
Stain resistance	5	
Resistance to cold food products	APTO	
Resistance to hot food products	APTO	
Fastness to rubbing	APTO	
Dimensional stability at elevated temperature	CUMPLE	
Climate shock test. resistance index	RESISTE	
Resistance to thermal shock	RESISTE	
Flammability	A1	
*ICO 12000-2015 UNE EN 14411-2017		

*ISO-13006:2015 UNE-EN 14411:2017



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

100332628 NYLO NOIR POLISHED

PORCELANOSA Grupo

ANTI-SLIP VALUE

	CEN/15 41901/02, DIN-51150 Y ASTIVI A157.1
Dynamic coefficient of friction	<0.42
Slip resistance (pendulum-wet)	CLO
Resistance to bacteria	ΑΡΤΟ
Resistance to cleaning products	APTO
Resistance to bathroom cleaning products	ΑΡΤΟ
Resistance to cigarette burns	APTO
Pendulum test value (ptv)	DRY>36-LOW_WET<25-HIGH
Slip resistance (pendulum-dry)	>40
*ISO-13006:2015 UNE-EN 14411:2017	

	PACKING
Sales units per box	3.240441 M2/BOX
Sales units per pallet	71.289695 M2/PAL
Sales units per unit	3.240441 M2/PIECE

ADDITIONAL NOTES

Avoid direct access from the outside if no abrasive protection device is provided.

SCOPE OF USE

Technical code-1 Technical code-2 1 - Coating 0 - No additional requirements



ACRES

SGS

SGS

SGS

Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.