


Model: PAONAZZO BIONDO POL. 120X270(6)(A)

Codes: 100332665

Absorption: Bla - Porcelánico (E<=0.1%)



## DIMENSIONAL FEATURES

UNE-EN ISO 10545-2

Length	2700 MM	
Thickness	6 MM	
Width	1200 MM	
Length and width deviation	Below 0.15%	+/-0.3%*
Side straightness deviation	Below 0.15%	+/-0.3%*
Squareness deviation	Below 0.15%	+/-0.3%*
Surface flatness deviation	Below 0.15%	+/-0.4%*

\*ISO-13006:2015 UNE-EN 14411:2017

## MECHANICAL FEATURES

UNE-EN ISO 10545-4-6-7-11

Breaking strenght	>1100 N	
Modulus of rupture	>45 N/MM2	-*
Abrasion resistance	<140	

\*ISO-13006:2015 UNE-EN 14411:2017

## HYGIENIC FEATURES

UNE-EN ISO 10545-13-14

Chemical resistance	MIN B	
Stain resistance	5	
Flammability	A1	

\*ISO-13006:2015 UNE-EN 14411:2017

## ANTI-SLIP VALUE

CEN/TS 41901/02, DIN-51130 y ASTM A137.1

Dynamic coefficient of friction	<0.42	
Slip resistance (pendulum-wet)	CL0	
4s	DRY>36-LOW_WET<25-HIGH	
Slip resistance (pendulum-dry)	> 40	

\*ISO-13006:2015 UNE-EN 14411:2017

## SCOPE OF USE

Technical code-1	Use on walls	
Technical code-2	Dry interior floors	

System Certification



## PACKING

Sales units per box	3.240441 M2/BOX	
Sales units per pallet	71.289695 M2/PAL	
Sales units per unit	3.240441 M2/PIECE	

## ADDITIONAL NOTES

Avoid direct access from the outside if no abrasive protection device is provided.

### System Certification



Do not use cleaning agents containing hydrofluoric acid.  
It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.  
For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double glueing technique.  
Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.