

Model: TANZANIA TAUPE 23X150(A) Codes: 100339756 Water absorption: BIa - Porcelanico (E<=0.1%)



Sistema DAPc[®] Declaración Ambiental de Productos de Construcción

	DIMENSIONAL UNE-EN ISO	
Thickness	11 MM	+/-5%*
Width	230 MM	
Length	1500 MM	
Length and width deviation	Below 0.15%	+/-0.3%*
Side straightness deviation	Below 0.15%	+/-0.3%*
Squareness deviation	Below 0.15%	+/-0.3%*
Surface flatness deviation	Below 0.15%	+/-0.4%*
*ISO-13006:2018 UNE-EN 14411:2016		
	MECHANICAL UNE-EN ISO 105	
Abrasion resistance	PEI 3 / 600v	

Crazing resistance

Resists 3 cycles

CL1

*ISO-13006:2018 UNE-EN 14411:2016

	HYGIENIC FEATURES UNE-EN ISO 10545-13-14:1995	
Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	B Min.*
Stain resistance	Class 5. Easy cleaning with water	3 Min.*
*ICO 1200C-2018 LINE EN 14411-201C		

ISO-13006:2018 UNE-EN 14411:2016

ANTI-SLIP VALUE EN 16165: 2022 / ASTM C1028

Slip resistance (pendulum-wet) *ISO-13006:2018 UNE-EN 14411:2016

	PACKING
Sales units per box	1.724971 M2/BOX
Sales units per pallet	41.399296 M2/PAL
Sales units per unit	0.344994 M2/PIECE
	SCOPE OF USE

Technical code-1

5 - Use on medium traffic floors



SGS

SGS

PORCELANOSA Grupo

RECOMMENDED USE LOCATIONS

Single-family dwelling

Indoor Premises - Dry: Room, room, bedroom or other enclosure without direct access to the outdoors.

Collective housing

Indoor Premises - Residential - Dry: Entrance, living room, dining room, professional office with reception of customers

Indoor Premises - Housing - Dry: Bedrooms, personal office, storage room, changing room

Various

Cladding of bonded or mixed facades

Facade cladding with mechanical anchors

Kitchen worktops, bars, restaurants

Public bathroom countertops



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.