

Model: TERRA TOPO L 120X120(A) Codes: 100348032 Water absorption: BIa - Porcelanico (E<=0.1%)



Sistema DAPc<sup>®</sup> Declaración Ambiental de Broductor de Construcción

		IAL FEATURES ISO 10545-2
Thickness	8.5 MM	+/-5%*
Width	1200 MM	
Length	1200 MM	
Length and width deviation	Below 0.15%	+/-0.3%*
Side straightness deviation	Below 0.15%	+/-0.3%*
Squareness deviation	Below 0.15%	+/-0.3%*
Surface flatness deviation	Below 0.15%	+/-0.4%*
*ISO-13006:2018 UNE-EN 14411:2016		

		AL FEATURES 0545-4-6-7-11
Breaking strength	2366 N	>1300N*
Modulus of rupture	53 N/MM2	>=35N/mm2*
Abrasion resistance	PEI 4 / 1500v	
Crazing resistance	Resists 3 cycles	
*ISO-13006:2018 UNE-EN 14411:2016		

	HYGIENIC FEATURES UNE-EN ISO 10545-13-14:1995	
Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	B Min.*
Stain resistance	Class 5. Easy cleaning with water	3 Min.*
*ISO-13006:2018 UNE-EN 14411:2016		

	ANTI-SLIP VALUE EN 16165: 2022 / ASTM C1028	
Slip resistance (pendulum-wet)	CL2	
Slip resistance (ramp)	R-10	TONO 1 / ID 2434*
Slip resistance (bare feet)	С	TONO 1 / 18733*
*ISO-13006:2018 UNE-EN 14411:2016		

	PACKING
Sales units per box	1.440092 M2/BOX
Sales units per pallet	60.483871 M2/PAL
Sales units per unit	1.440092 M2/PIECE



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

100348032 TERRA TOPO L



# SCOPE OF USE

Technical code-1

6 - Use on heavy traffic floors



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

# PORCELANOSA

# **RECOMMENDED USE LOCATIONS**

#### Single-family dwelling

Outdoor Premises: Porches, verandah, terrace, outdoor access or circulation area

Indoor Premises - Dry: Entrance and other enclosures with direct opening to the outside (garden, terrace, storage room).

Indoor Premises - Dry: Individual staircase

Indoor Premises - Wet: Kitchen, mini kitchen in living area, laundry room

Indoor Premises - Humid: Bathroom or Toilet

# Collective housing

Outdoor premises: Balconies, terraces, galleries (not accessible from the outside)

Indoor Premises - Common Elements: Entrance Hall (less than 15 dwellings)

Interior Premises - Common Elements: Entrance Hall (more than 15 dwellings)

Indoor Premises - Common Elements: Stairs and corridors with or without lifts

Indoor Premises - Common Elements: Meter centralisation room

Indoor Premises - Common Elements: Storage rooms for children's cars, bicycles, etc.

Indoor Premises - Dwelling - Damp: Kitchen, mini kitchen and living area, laundry room

Indoor Premises - Dwelling - Damp: Bathrooms or shower rooms

#### Public Residential

Single or double rooms

Group rooms

Intensive use dormitories in residences, schools, etc.

## Administrative

Office with workstation

Collective office, open plan office

Meeting/conference room, shops and retail (sales area)

Shops, warehouses with average public attendance (sales area)

Department stores, hypermarkets, shopping centres (sales area)

#### Commercial

Shops and retail trade (Sales area)

Shops, warehouses with average public attendance (sales area)

Department stores, shopping centres (sales area)

#### Teacher

Pre-school and Primary: Classroom without direct opening to the exterior

Infant and Primary: Playroom, exercise, multi-purpose room without direct opening to the outside

Secondary, Baccalaureate and University: Classroom without direct opening to the outside.

Secondary, Baccalaureate and University: Multi-purpose classroom, meetings

Secondary, Baccalaureate and University: Other laboratories (physics, electricity, radiation, mechanics).

## Sanitary

Single-user room, isolation room

Collective room

Waiting rooms, consultation rooms, distribution corridors

Major and minor operating theatres. Operating theatres

Radiological premises

Rehabilitation, massage, therapy and rehabilitation centres

Laboratories (no public access)

## Public attendance

Catering: Main dining room, banqueting hall (intensive use)

Catering: Dining room restaurant, bar, cafeteria (medium use)

Catering: Dining room, company cafeteria

Entertainment and recreation: Large hall for receptions, dances, discotheques. Intensive use

Entertainment and recreation: Showroom, cinema, theatre, sports activities, amphitheatres, games (Closed)

Entertainment and recreation: lounges, waiting room, TV lounge, games room

Libraries and reading rooms: Libraries, reading rooms, temples of worship, museums (With public access)

Libraries and reading rooms: Libraries, reading rooms, houses of worship, museums (Internal use)





Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.



# Common transit areas

Indoor premises: corridors and common areas with heavy traffic

Indoor premises: Corridors and common areas with average traffic

# Service, facilities

Toilets in office areas, restricted use

Sanitary premises special hygiene (hospitals, food)

Premises for telephone, computer and other dry installations

Re-printing service, copies of plans, photography

Archive and storage premises



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.